



Grout Shine

Glitter for Epoxy Grout

Product Description:

MagicBond – Grout Shine is used to give a glittery effect and enhance the beauty of the tiles and stones. It is to be used with Epoxy Tile Grout EG -100 and is suitable for internal and external areas under wet & dry conditions on wall & floor.

Suitable For:

Variety of tiles and stones – Ceramic, Vitrified, Marbles, Granites, Large Format Tiles, Stones, etc.

Advantages:

- Acid Resistant
- Sparkling Joints
- Water Resistant
- Stain Free
- Chemical Resistant
- Eco Friendly
- Easy To Use

Packaging: 100 g bottle

Appearance: Available in Gold, Copper and Silver color.

Dosage: 50g of Grout Shine to be added to 1kg of Epoxy Tile Grout EG – 100 (Resin + Hardener + Filler)

TECHNICAL DETAILS

Melting Point	>170°C
Water Solubility	Insoluble
Bulk Density	0.4 – 0.5 g/ cc
Mixing Density (EG-100+Sparkles)	1.75 ± 0.05 Kg/ liter
Pot life @ 30°C	Approx. 60 minutes
Joint Width	2-15 mm
Application Temperature	+10°C to +35°C
Regular Traffic	72 hours
Light Traffic	24 hours
Sag Resistant	No Sag

Specifications are subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on application methods and site conditions.

Shelf Life:

Factory packed pouch of MagicBond – Grout Shine carries a shelf life of 36 months, if stored in cool & dry place.

INSTALLATION

Surface Preparation:

Before starting to grout remove the dirt and dust from tile surface by cleaning with the provided sponge.

Mixing:

Pour Part A hardener in Part B in a bucket. Mix both parts carefully with the help of a mechanical stirrer until a smooth mixture is obtained. Add required content of Part C (Epoxy Grout Filler Powder) for desired consistency. Then add the MagicBond – Grout Shine part till a uniform colour and

lumps free consistency is achieved.

- Acid is not recommended to clean the joints, use MagicBond – CleanPRO for cleaning purpose.

Application:

Start filling the joints with Epoxy Tile Grout using a rubber float. Hold the rubber float perpendicular to the surface to remove excess grout. Every 20-40 minutes check for joints that are to be hardened. For clean-up use a wet towel on the surface until the oily feel is gone. Repeat the process with the wet towel after 12 - 24 hour to remove the remaining haze. Water and shampoo solution is also preferable for a better surface clean up.

Cleaning:

Excess adhesive needs to be cleaned with water or alcohol when it is still fresh.

Once cured, it can only be removed with the help of mechanical means.

Safety Precautions:

- Apply on completely dry tile joints.
- Take care that water does not flow or run to the un-grouted joints while application.
- Protect the grouting for at least 24 hours from direct sunlight or traffic.
- Do not over mix the material, it can reduce the pot life.
- Change the cleaning cloth/sponge when they are impregnated with grout.

Limitations:

- Not recommended to be used with cement based tile grout.
- Do not use it on aggressive prone areas and the areas which are subjected to aggressive pressure cleaning.